

PHOTO **SMOOTH PEARL** 290

PRODUCT DESCRIPTION

Fotospeed PHOTO SMOOTH PEARL 290 is a bright white, heavyweight and instant dry, resin coated, inkjet paper. The beautiful pearl finish matches that of the widely acclaimed, and now discontinued, Ilford Gallerie Smooth Pearl paper; a crisp finish with a superb colour gamut

It has a unique ink receiving layer giving an instant dry result straight from the printer.

Compatible with both Dye and Pigment ink.

FEATURES

- **Bright white finish**
- **Professional Pearl surface**
- **HDR precision coated**
- **Heavy-weight look and feel**
- **Instant dry**
- **Pigment and Dye ink compatible**
- **Excellent colour gamut for colour photography**
- **Exceptional D-max**

TECHNICAL INFORMATION

| | |
|---------------------|------------|
| Thickness (Microns) | 290 |
| Weight GSM | 290 |
| Coating Type | Semi-Gloss |
| OBA | Moderate |
| Whiteness (CIE) | 140 |
| Brightness (TAPPI) | 84 |
| pH | 8.5 |
| Opacity | 90% |
| Recyclable | Yes |

MEDIA AVAILABILITY

| Rolls | 17" | 24" | 36" | 44" | 60" |
|--------|-----|-----|-----|-----|-----|
| | ✓ | ✓ | ✓ | ✓ | ✓ |
| Sheets | A4 | A3 | A3+ | A2 | |
| | ✓ | ✓ | ✓ | ✓ | |

APPLICATIONS

- Proofing
- Water Resistant Prints
- Professional Photographic Images
- Presentations

STORAGE AND CONDITIONS OF USE

- The storage of all papers should take place in a recommended climate of 15-25c, relative humidity of 40c.
- 60 %, and out of direct sunlight.
- Do not exceed temperatures of 82c (180f) when dry mounting.

PAPER HANDLING

- Return unused paper to the original box and store flat. If storing the paper outside the original box, only use archival packaging.
- Leave papers open to the air to fully dry for a few hours after printing, (24 hours are recommended) and avoid stacking on top of each other straight away.